



## ▶ DPF 510GTX/MTX Vinyl Film

### Digital Print Pressure-Sensitive Vinyl Film

DPF 510GTX/MTX is a 3.2-mil (80 micron) calendered film with a tinted, solvent-based pressure-sensitive adhesive and a low profile air-egress, lay-flat liner. X-Scape Technology® enables trapped air to escape through the air channels for an speedy installation and a smooth finished graphic. The high-quality adhesive provides far superior adhesion and cohesion properties than water-based adhesive. DPF 510GTX/MTX is available in a gloss and matte finish. DPF 510 is rated for outdoor durability up to 3 years (unprinted). Printed durability is dependent on the ink system used.

### APPLICATIONS & FEATURES

- X-Scape Technology® for easy installation and a smooth finish
- Short-term promotional and display graphics
- Excellent printability on Eco-Solvent, Solvent and Latex print systems.
- Ideal for interior and exterior applications on flat surfaces.

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	70 to 90 Gloss Units (Gloss) Up to 30 Gloss Units (Matte)	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	3.2-mil (80 micron)	
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 12 lb/in	≥ 2.14 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	≥ 150%	
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	1 year from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	50°F to 90°F	10°C to 32°C
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-20°F to 150°F	-29°C to 65°C
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours	10-mil	0.25 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, 70°F (21°C)	≥ 1.50 lb/in	≥ 0.26 kg/cm
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	70 g/2 in	13.8 g/cm

Standard Terms & Conditions Apply

## TERMS & CONDITIONS

*The following is made in lieu of all warranties expressed or implied:*

All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.

March 2019